

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

10/531690

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
29 April 2004 (29.04.2004)

PCT

(10) International Publication Number  
WO 2004/035853 A1

(51) International Patent Classification<sup>7</sup>: C23C 8/22,  
C21D 1/76

[PL/PL]; ul. Chochola 43, PL-91-230 Łódź (PL). OLE-  
JNIK, Józef [PL/PL]; Osiedle Zaków 61, PL-66-200  
Swiebodzin (PL). HEILMAN, Paul [DE/DE]; Tiedstrasse  
8, 63469 Maintal (DE).

(21) International Application Number:  
PCT/PL2003/000066

(22) International Filing Date: 2 July 2003 (02.07.2003)

(74) Agent: NISZTUK, Helena; Lubuski Klub Techniki i  
Racjonalizacji, ul. Niecała 2F, PL-65-245 Zielona Góra  
(PL).

(25) Filing Language: English

(26) Publication Language: English

(81) Designated State (national): US.

(30) Priority Data:  
356754 21 October 2002 (21.10.2002) PL

(84) Designated States (regional): European patent (AT, BE,  
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,  
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

(71) Applicants (for all designated States except US):  
SECO/WARWICK SP. Z O.O. [PL/PL]; ul. Sobieskiego  
8, PL-66-200 Swiebodzin (PL). POLITECHNIKA  
ŁÓKZKA [PL/PL]; ul. Stefanowskiego 1/15, PL-90-924  
Łódź (PL).

Published:  
— with international search report

(72) Inventors; and  
(75) Inventors/Applicants (for US only): KULA, Piotr

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: HYDROCARBON GAS MIXTURE FOR THE UNDER-PRESSURE CARBURIZING OF STEEL

(57) Abstract: The subject of present invention relates to mixture for carburizing of steel products, mainly parts of machines, vehi-  
cles and every mechanical apparatus, used in vacuum furnaces. Present invention relates to mixture for under-pressure carburizing  
containing the carbon carrier comprising two unsaturated hydrocarbons, likely ethylene and acetylene, in volume ratio from 0.1 to  
2.00. The carbon carrier can be further mixed with hydrogen or ammonia.

WO 2004/035853 A1

## HYDROCARBON GAS MIXTURE FOR THE UNDER-PRESSURE CARBURIZING OF STEEL

The object of the present invention relates to a mixture used in vacuum furnaces for under-pressure carburizing of steel products, mainly parts of machines, vehicles and all sorts of mechanical apparatuses.

From the US Patent 5,702,540 a process is known, in which a charge is processed under vacuum in the presence of a carbon carrier which contains unsaturated aliphatic hydrocarbons, where the pressure in the chamber shall not be higher than 1 kPa.

Another US Patent, 6,187,111, uses gaseous ethylene as the carbon carrier and the pressure in the chamber shall be within the range of 1 to 10 kPa, whereas the charge shall have the temperature between 900°C and 1100°C.

The patent EPO 0,882,811 is also known in which the carbon carrier is a hydrocarbon with a strict 1:1 carbon-to-hydrogen ratio.

To obtain the required carburizing result the carbon carrier, ethylene or acetylene, is introduced to a hot vacuum furnace chamber during the carburizing stage either in a continuous or a pulse manner. The carbon carrier can be introduced together with other chemically inert gases, e.g. nitrogen, argon, or active gases, e.g. hydrogen, in order to control the efficiency and cleanness of the carburizing process, as well as with active nitrogen carriers, e.g. ammonia, for carbonitriding of steel.


The main point and essence of the present invention is the mixture for under-pressure carburizing, which contains the carbon carrier in the form of two unsaturated hydrocarbons, having the volume ratio from 0.1 to 2.00, preferably from 0.15 to 2.0. The carbon carrier is preferably ethylene and acetylene. The carbon carrier can be further mixed with hydrogen or also with ammonia. In the case of mixing the carbon carrier with hydrogen, 0.7 to 1 volume by ratio should be maintained. For ammonia this ratio is 0.7 to 5.0.

The mixture according to the present invention is characterized by the effect of synergy of uniform carburizing of intricate shape workpieces, especially those with narrow and deep hollows of complicated shapes and recesses, and effective elimination of side-products of vacuum carburizing of steels such as soot and tar.

One of possible implementations of the mixture for under-pressure carburizing according to the present invention is illustrated by the following examples, while the surfaces of the samples are shown in the figure enclosed.

### **Example 1**

A furnace chamber of the size 200x200x400 mm was charged with workpieces made of low carbon steel grades together with three samples made of 16CrMn5 with deep, narrow hollows of intricate shapes. The total surface area of the charge was 0.4 m<sup>2</sup>. After heating under vacuum up to 950°C the carbon carrier was introduced - comprising ethylene and acetylene in the volume ratio 1, mixed with hydrogen in the volume ratio 1,17 - with constant flow rate 190 l/hr and pressure pulse was generated in the furnace chamber within the range of 3 to 8 mbar. Steel workpieces were heated 20 minutes under this atmosphere at the temperature of 950°C, then under vacuum for 10 minutes and they were then cooled down to the ambient temperature. On the surface of all the samples including the entire cross section of the deep hollow of intricate shape, the carburizing layer was formed. The layer was of a uniform perlitic structure without precipitation of secondary carbides and of a uniform depth of  $0.44 \pm 0.05$  mm measured according to the limit structure of 50% perlite and 50% ferrite. No evidence of soot and tar was found either on the surface of workpieces after carburizing or in the furnace chamber interior.



### Example 2

A furnace chamber of the size 200x200x400 mm was charged with workpieces made of low carbon steel grades together with three samples with made of 17CrNi with deep, narrow hollows of intricate shapes. The total surface area of the charge was 0.4 m<sup>2</sup>. After heating under vacuum up to 950°C the carbon carrier was introduced - comprising ethylene and acetylene in the volume ratio 1.83, mixed with hydrogen in the volume ratio 1,45 - with constant flow rate 208 l/hr and pressure pulse was generated in the furnace chamber within the range of 3 to 8 mbar. Steel workpieces were heated 20 minutes under this atmosphere at the temperature of 950°C, then under vacuum for 30 minutes, and then fast cooled to the ambient temperature under 6 bar nitrogen pressure. On the surface of all the samples including the entire cross section of the deep hollow of intricate shape, the carburizing layer was formed. The layer was of a uniform martenzitic structure without precipitation of secondary carbides and of a uniform depth of  $0.46 \pm 0.05$  mm measured according to the minimum limit hardness of 500 HV<sub>01</sub>. No evidence of soot and tar was found either on the surface of workpieces after carburizing or in the furnace chamber interior.

**CLAIMS:**

1. The mixture for under-pressure carburizing employing hydrocarbons is **characterized in that** it contains the carbon carrier in the form of two unsaturated hydrocarbons in the proportion from 0.1 to 2.0, where the said carbon carrier can be further mixed with other components modifying the carburizing process.
2. The mixture for under-pressure carburizing according to claim 1 is **characterized in that** it is beneficial and preferable to have the said hydrocarbons in the proportion of from 0.15 to 2.0.
3. The mixture for under-pressure carburizing according to claim 1 is **characterized in that** it is most beneficial and preferable if the said carbon carrier is a mixture of ethylene and acetylene.  
the said carbon carrier should preferably be a mixture of ethylene and acetylene
4. The mixture for under-pressure carburizing according to claim 1 is **characterized in that** the said carbon carrier can be mixed with hydrogen in the proportion from 0.7 to 1.6.
5. The mixture for under-pressure carburizing according to claim 1 is **characterized in that** the said carbon carrier can be mixed with ammonia in the proportion from 0.7 to 5.0.

# INTERNATIONAL SEARCH REPORT

Inter. Application No  
PCT/PL 03/00066

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 C23C8/22 C21D1/76

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C23C C21D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, METADEX, PAJ, WPI Data, COMPENDEX

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 04; 31 August 2000 (2000-08-31) & JP 2000 001765 A (NACHI FUJIKOSHI CORP), 7 January 2000 (2000-01-07)	1-3
Y	paragraph 24 of patent document abstract	4,5
Y	EP 0 818 555 A (JH CORP) 14 January 1998 (1998-01-14) column 4, line 3-13,45-50	4,5
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&\* document member of the same patent family

Date of the actual completion of the international search

15 January 2004

Date of mailing of the international search report

04/02/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Badcock, G

# INTERNATIONAL SEARCH REPORT

Inter Application No  
PCT/PL 03/00066

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	KULA, P. (TECHNICAL UNIVERSITY OF LODZ) ET AL: "New vacuum carburizing technology." HEAT TREATING PROGRESS (FEB.-MAR. 2001) 1, (1), 57-60, GRAPHS, PHOTOMICROGRAPHS, 6 REF., XP009023937 page 58-59	4, 5
A	----- SUGIYAMA M ET AL: "VACUUM CARBURIZING WITH ACETYLENE" ADVANCED MATERIALS & PROCESSES, AMERICA SOCIETY FOR METALS. METALS PARK, OHIO, US, vol. 155, no. 4, April 1999 (1999-04), pages H29-H33, XP000866805 ISSN: 0882-7958 page 2 -page 3	1-5
A	----- PATENT ABSTRACTS OF JAPAN vol. 2002, no. 11, 6 November 2002 (2002-11-06) & JP 2002 194526 A (DOWA MINING CO LTD), 10 July 2002 (2002-07-10) abstract -----	1-5

# INTERNATIONAL SEARCH REPORT

on patent family members

International Application No

PCT/03/00066

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2000001765	A	07-01-2000	NONE
EP 0818555	A	14-01-1998	AT 203063 T 15-07-2001
		CA 2215897 A1 03-10-1996	
		DE 69613822 D1 16-08-2001	
		DE 69613822 T2 04-04-2002	
		EP 0818555 A1 14-01-1998	
		CN 1184510 A 10-06-1998	
		JP 2963869 B2 18-10-1999	
		JP 8325701 A 10-12-1996	
		WO 9630556 A1 03-10-1996	
		TW 400394 B 01-08-2000	
		US 5702540 A 30-12-1997	
JP 2002194526	A	10-07-2002	NONE